



Lightfast fatliquoring agent for Nappa, Garment, Upholstery & other very soft leather types

CHARACTERISTICS:

Chemical Composition	:	Aliphatic hydrocarbon and alcohols sulfonated by special methods.
Aspect	:	Free flowing brown liquid.
Active Matter	:	65% ± 2
pH(10% emulsion)	:	8.0 - 9.0
Lightfastness	:	Excellent.
Stability	:	Stable to neutral salts, bases, acids and chrome salts at usual concentration. Compatible with anionic dyes as well synthetic and vegetable tanning agent.
Storage Stability	:	9 -12 months when properly stored.

PROPERTIES & APPLICATION:

VICASTOL 94 V is having the property of excellent lightfastness and heat resistance. It provides extreme inner softness alongwith pleasant & silky touch to leather.

VICATOL 94 V has capacity to disperse retanning material and dyes, hence gives leather with round body, good feel & mellowness to the leather.

VICASTOL 94 V having some bleaching property with neutral odour, hence suitable for white and pastel shades leather. when use in higher percentage, has uptake completely and thereby gives extreme softness to the lather without greasiness on surface.

VICASTOL 94 V is highly recommended for garment, upholstery, gloving and milled leather etc.

VICASTOL 94 V can be use 2-10% depending upon type of leather to be produce and required result.